Grading Urban Hardwood Lumber

Peter Tittmann

UC Berkeley Center for Forestry Wood Resources Group

California Urban Forests Council Annual Meeting April 2, 2015

Wood Resources Group

Public outreach and education Workshops, fact-sheets and publications:

- Wood bioenergy public benefits.
- Wood properties and processing.
- Bioenergy conversion technologies.
- GHG balance from wood bioenergy.
- Harvesting and transportation cost and logistics.

Technical assistance Businesses and community organizations.

- Project development
- ▶ Technology due diligence

Research Forest bioenergy systems

- ► Evaluate potential for small scale distributed gasification + electricity generation
- Investigate maximum potential for carbon sequestration from CA forests
 Berke

Resource Library: Hardwood Properties

Hardwood Handbook

- Drying
- Properties
- Milling
- Stacking and Loading
- Quality Control

Sudden Oak Death

- Processing tanoak (Notholithocarpus densiflorus)
- Heat treatment

California Hardwoods Video







What are grades?

Lumber grades establish a hierarchy of quality for a general application based on a set of standards





Why grade lumber?

Primary Function Establish a **fungible** product. Transactions can be conducted without visual inspection of the product with confidence that the product meets established quality standards.

Secondary (not necessarily) Marketing. Proprietary grades can be used to differentiate products in a crowded market.

Also... Typically required in permitted structural applications

Standards vs. grades

Standards Establish performance characteristics

 American Lumber Standards Committee (ALSC) ensures impartial/unbiased grading

Grades Establish a hierarchy of quality based on standards

- Many organizations develop grades, some more widely used than others. Typically grades reference ALSC standard
- Sets thresholds for:
 - Moisture content
 - Measurement and Tally
 - Lumber dimensions
 - Marking
 - Visual characteristics (knots, wane, warp)

Grading Softwoods vs Hardwoods

Softwoods Whole board

- Structural applications, strength properties
- Necessary but not required for sale into commodity lumber markets

Hardwood Usable content.

 Visual/aesthetic applications: knots, grain, wane, warp

Hardwood Grades

National Hardwood Lumber Association (http://www.nhla.com/)

Factory lumber Intended for remanufacturing. Grades based on the number and quality of pieces that can be cut from the board of a minimum size. Milled to within dimension ranges specified by grade. Examples: kiln-dried, unfinished lumber

Dimension and component parts Intended for little or no remanufacturing. Machined to specific dimensions. Examples: flat stock, rough squares

Finished market products Machined for final use. Examples: Flooring, architectural millwork





Factory grades


FAS(Firsts and Seconds), **F1F** (FAS one side)

- FAS
- ▶ Minimum board size 6 in × 8 ft
- >83% clearwood cutting not smaller than 3 in×7 ft or 4 in × 5 ft
- Both sides
- F1F Same as FAS on 1 side, other side must meet #1 Common

Selects Same as F1F but minimum board size is 4 in \times 6 ft




Note: Minimum yield 831/2% clear wood cuttings on the poor face of the board.



Factory grades

No. 1C "Cabinet" ► Minimum board size 3 in × 4 ft

- > >66% >83% clearwood cutting not smaller than 3 in×3 ft or 4 in \times 2 ft
- ▶ Both sides same




American Hardwood Export Council (aehc.org)


Factory grades

No. 2C "Economy" Same as FAS on 1 side, other side must meet #1 Common

- Minimum board size 3 in × 4 ft
- > >50% >66% clearwood cutting not smaller than 3 in×3 ft or 3 in × 2 ft
- If best side is 2C, other side can be any.



Note: If the better face meets the requirements for either FAS or Number 1 Common and the poor face grades Number 2A Common, the grade of the board is Number 2A Common.



There are lower NHLA grades than Number 2A Common but they are usually converted into dimension parts, flooring parts, or used domestically in the USA.





Hardwood Consumption by Market Sector

Estimates of Consumption of US Hardwoods											
© 2013 Hardwood Market Report											
										%	%
	2005	2006	2007	2008	2009	2010	2011	2012	2013	Change 2012	Change 2005
Pallets	3.8	3.7	3.6	3.5	3.0	3.2	3.26	3.27	3.572	9.2%	-6.0%
Furniture	1.2	1.1	1.0	0.7	0.3	0.35	0.29	0.30	0.372	24.0%	-69.0%
Exports	1.3	1.3	1.2	0.9	0.8	1.07	1.2	1.32	1.436	8.8%	10.5%
Millwork	1.3	1.2	1.0	0.7	0.4	0.43	0.24	0.26	0.314	20.8%	-75.9%
Cabinets	1.6	1.5	1.3	1.2	0.7	0.4	0.34	0.36	0.388	7.8%	-75.8%
Flooring	1.5	1.4	1.3	0.8	0.5	0.59	0.51	0.55	0.636	15.6%	-57.6%
Railway Ties	0.85	0.96	0.92	0.94	0.89	0.89	0.98	1.04	1.007	-3.2%	18.5%
Board Road/Mat Timbers	N/A	N/A	N/A	0.2	0.05	0.075	0.12	0.16	0.248	55.0%	NA
Total Estimated Consumption	11.55	11.16	10.32	8.94	6.64	7.01	6.94	7.26	7.97	9.8%	-37.1%
Billion Board feet											




Graded Hardwood Consumption Trends





Hardwood Prices



Urban Wood Cost

Expensive!





Grading Urban Hardwoods



Why grade urban hardwood lumber?

Communicating with buyers. Basis for conveying familiar quality standards.

but...

may be missing the point







Black walnut

Sycamore

Cherry

All the same grade...

Marketing vs Grading

For unique woods (origin, aesthetic, quality), grade should not be a substitute for **a story**Stories can be built around:

- History
 - ▶ Figure
 - ► Color, grain
 - ► Provenance (geographic origin)
 - Cultural/personal meaning

Urban wood application



Source: Urban Lumber Co. (www.urbanlumber.co)



In summary

- Grading can be useful selling sight-unseen into commodity markets
- Useful to generally know grading rules
- Wont help differentiate the wood based on uniqueness/distinctiveness

Questions?

Contact information

Peter Tittmann, Ph.D. Center for Forestry UC Berkeley pwt@berkeley.edu o. (510) 665-3518 c. (707) 849-4135

web: http://ucanr.edu/sites/WoodyBiomass/

twitter: @UCBWoodProducts

This work is funded in part through a Cooperative Agreement with the USDA Forest Service.